Product Data Sheet Screen Printing Ink





Solvent Based Screen Ink Range, 1- and (alternatively) 2-Component

APPLICATION

Screen printing ink, mainly for decoration of containers (cans, tubes and cartridges), various promotional, and souvenir items. YN inks are especially suitable for printing of thermoplastics made of pre-treated polyolefines, i.e. polypropylene (PP) and polyethylene (HD-PE, LD-PE), also for duroplastics, rigid PVC and polystyrene (PS), coated substrates, metal and Chromolux paper.

PROPERTIES

- Screen inks YN are solvent based screen printing inks. They can be processed as 1-component and (alternatively) as 2-component ink with hardener.
- Processed as 1-component ink YN dries physically, as 2-component ink physically chemically-reactive and results in a glossy finish.
- Processing as 2-component ink (=with hardener) will further increase ink adhesion properties on difficult substrates such as pre-treated PP/PE.
- This ink system shows good resistance against filling products, e.g. cosmetics and chemicals, especially when processed as 2-component ink with the addition of hardener.
- YN inks are suitable for medium-term outdoor applications.
- Note: Because of the variety of substrates, pre-tests are essential. It is also advised to check efficiency of
 possibly required pre-treatment of substrates (cleaning/degreasing, flame/corona/plasma treatment) or
 maybe even post-treatment (flame-drying).

COLOUR SHADES - OVERVIEW

Mixing System: C-MIX 2000
 12 colour shades for mixing of RAL, PMS and HKS colours.

Opaque: Standard Colour shades with medium to good opacity.

Standard HD Highly opaque colour shades.

Process Inks: "180" colours 4 transparent colour shades according to ISO 2846-4.

Bronzes: B / AB / MG Gold, silver and copper shades.

- Special colour shades are available upon request.
- More information about available colour shades in the detailed tables in section Colour Shades.

CHOICE OF PIGMENTS AND LIGHT FASTNESS

Colour shades of YN ink range contain pigments with a high light fastness. Light fastness and weather resistance will reduce if thinner layers are applied or if base colours are mixed with a high ratio of white or varnish.

Applied on suitable substrates YN inks are suitable for medium-term outdoor applications.

ADJUSTMENT FOR SCREEN PRINTING

- Screen printing inks YN are not supplied in a ready-to-print adjustment.
- Processed as 1-component ink (without addition of hardener):
 Ink is adjusted to printing consistency by addition of thinner or retarder (stir with mixer or agitator).
- Processed as 2-component ink (with addition of hardener):

As 2-component ink YN inks have to be mixed with hardener at a specified ratio prior to processing. Thinner is added after addition of hardener.

The mixed ink should be allowed to pre-react for approx. 15 minutes prior to processing (recommendation). Processing is then possible for a specified period of time (=pot life).

Hardener:

Alternatively, screen inks range YN can be processed with hardener Z/H.

Hardeners are sensitive to humidity. Therefore, containers always have to be tightly closed.

Addition of hardener Z/H to YN inks is 10 parts ink: 1 part hardener (parts by weight).

Pot life:

- Ink mixed with hardener Z/H may only be processed within a limited period of time (=pot life)
- Pot life of YN + hardener Z/H is up to 10 h (at 20°C).
 Higher temperatures will reduce pot life.
- We do not recommend processing the inks for longer than the pot life as adhesion and resistance properties will then continually deteriorate, even if the ink still seems to be liquid and processable.

THINNERS / RETARDERS

Depending on local conditions ink is adjusted to printing consistency by addition of 15 - 25 % of thinner or retarder.

For adjustment of screen inks YN, the following products are available:

| Thinner: | 0 | VD 30 | Standard thinner |
|-----------|--------------|--------------|------------------------------|
| | • | VD 60 | Standard thinner (low odour) |
| Retarder: | • | VZ 25 | Medium retarder |
| | 0 | VZ 40 | Very slow retarder |
| | ■ = F | Preferred | O= Suitable |

Depending on printing conditions, the products listed above can be mixed into the inks individually or as mixtures. Please note that depending on evaporation rate of the thinner/retarder used drying times may be longer.

Thinner/retarder should be mixed into the ink thoroughly using a mixer or agitator. In addition, inks should be stirred well prior to each processing to obtain a homogeneous dispersion of all ingredients

ADDITIONAL AUXILIARY AGENTS

| Application | Product | Addition in % by weight | Additional Information |
|--------------------|-------------------|-------------------------|---------------------------------|
| Retarder paste | YN/VP | Max. 10% | Possibly slightly reduced gloss |
| | LAB-N 111420/VP | Max. 10% | Possibly slightly reduced gloss |
| Viscosity increase | Thickening powder | Max. 3% | Stir with mixer |
| Matting | Matting powder | Max. 5% | Stir with mixer |
| Flow agent | VM 1 | 3 to 5% | Do not overdose! |

OVERPRINTING

Generally, it is not necessary to overprint YN inks with varnish. However, overprinting to increase resistances of ink layers is possible with YN/E50.

BRONZE COLOURS, MIXING OF BRONZE INKS

Bronze colours 75/AB to 79/AB and metal gloss colours 75/MG to 79/MG are available.

Printers can mix bronzes themselves using bronze pastes B 75, B 76, B 77 and B 79 as well as bronze powder B 78-POWDER. For examples of colour shades please refer to our Bronze Colour Card.

These "B" bronze pastes and "B" bronze powder are mixed with bronze binder YN/B or varnish YN/E50 prior to processing.

Mixing ratios in parts by weight:

Gold bronze paste/powder to YN/B or YN/E50 = 1: 3-4Silver bronze paste to YN/B or YN/E50 = 1: 4-5

Contrary to AB and MG bronze colours, B bronzes are prone to oxidation (exception B 78-POWDER. Therefore, they should be overprinted, e.g. with YN/E50.

B 78-POWDER does not tend to oxidation. The pale copper shade will not darken with time. Colour of inks mixed with B 78-POWDER is similar to colour 78/AB as shown on our "bronze colour card".

Note: When overprinting bronze colours (B/ AB/ MG) with varnish or other colour shades, it is essential to carry out pre-tests to check intermediate adhesion of the ink layers (fingernail test, tape test).

DRYING / HARDENER REACTION

- Processing <u>WITHOUT</u> addition of hardener: Ink dries physically, i.e. by evaporation of solvents.
- Processing <u>WITH</u> addition of hardener Z/H:
 First, ink dries physically, followed by chemical cross-linkage reaction.

Drying and reaction temperature of hardener must be at least 15°C!

Drying

Drying times below are only approximate as drying properties depend on various factors:

- Type and amount of thinners/retarders used.
- Thickness of printed ink layer.
- Drying temperature.

Depending on local conditions, drying time in a drying frame (rack) is approx. 20 minutes at room temperature (20°C). Drying time with heat application (hot air fan/oven) is about 60 seconds at a temperature of 50°C.

Note: Addition of retarders may result in much longer drying times!

Hardener Reaction

Basically, the special adhesion and resistance properties of the ink are achieved only by chemical cross linkage reaction between ink and hardener. This cross linkage reaction depends on time and temperature.

The following are guide values only:

| Temperature | Time approx. | Condition of ink | Condition of ink film | |
|------------------|----------------|-----------------------------------|--|--|
| <15°C air drying | | Hardener Z/H does not react! | Ink film will not achieve any resistance | |
| 20°C air drying | 20 min. | Dry enough for overprinting | No increase of resistance yet | |
| | >72h | High degree of cross-linkage | Very high resistance values achieved | |
| | >5 days | Maximum cross-linkage | Maximum resistance achieved | |
| 80°C oven curing | approx. 5 min. | Dry enough for overprinting | No resistance yet | |
| | 60 min. | Very high degree of cross-linkage | Very high resistance values achieved | |

Resistance Tests

When processing YN inks with hardener Z/H resistances should not be checked before the ink has fully cured/cross-linked: Drying with 20°C/5 days, with 80°C/>60 minutes.

SCREEN FABRIC / STENCILS

YN inks have been formulated for printing with fabrics ranging from 77 to 120 threads/cm. Suitability for printing with coarser or finer fabrics should be determined by corresponding pre-trials.

All copy emulsions and capillary films suitable for solvent based screen inks can be used, such as our program of SunCoat or Murakami products.

CLEANING

Stencils and tools can be cleaned with our universal cleaning agents URS or URS 3.

When processing as 2-component system, the longer inks dry on stencils and tools the harder will be their removal due to the chemical cross-linkage reaction. Therefore, always clean stencils and tools as soon as possible. Thinner VD 40 can be used to remove persistent ink residues.

PACK SIZE

Screen printing inks YN are delivered in 1 litre containers. Other pack sizes are available upon request.

SHELF LIFE

In closed original containers, YN inks generally have a shelf life of 3 years from date of production. Hardener Z/H has a shelf life of 14 months from date of production, also in closed original containers.

For exact date of expiry, please refer to the label.

SAFETY DATA SHEETS

Read safety data sheet prior to processing

Safety data sheets comply with Regulation (EC) No. 1907/2006 (REACH), Appendix II.

CLASSIFICATION AND LABELLING

Hazard classification and labelling comply with Regulation (EC) No. 1272/2008 (CLP/GHS).

CONFORMITY

Coates Screen Inks GmbH does not use any of the substances or mixtures for the production of printing inks, which are banned according to the EUPIA (European Association of the Printing Inks Industry) exclusion policy. Screen printing inks range YN standard shades, C-MIX 2000 colour shades, standard, highly opaque standard colours (HD), process colours, silver, fluorescent colours and transparent colours comply with the requirements of toy standard "EN 71-3:2019 Safety of toys – Migration of certain elements (category III: scraped off material). Further compliance confirmations are available upon request.

ADDITIONAL INFORMATION ABOUT OUR PRODUCTS

Product data sheets: Auxiliary Agents for Screen Printing HM Brochures: Solvent Based Screen Printing Inks

Internet: Various technical articles are available for download on www.coates.de,

section "SN-Online"; e.g. processing of 2 component inks

FOR COLOUR RANGES, PLEASE REFER TO NEXT PAGE.

COLOUR SHADES

| OLOUR SHADES | | | | | | | | | |
|---|--------------|-------------------|--|-----------------|-----------------|--|--|--|--|
| | | | COLOUR SHAD | | e) | | | | |
| Mixing system for matching of PMS, HKS, RAL colours (on white substrates) Start formulations available in data base "Formula Management C-MIX 2000" | | | | | | | | | |
| | | According to cold | our card C-MIX 2000 | | | | | | |
| primrose | YN/Y30 | red | YN/R50 | green | YN/G50 | | | | |
| golden yellow | YN/Y50 | magenta | YN/M50 | black | YN/N50 | | | | |
| orange | YN/O50 | violet | YN/V50 | white | YN/W50 | | | | |
| scarlet | YN/R20 | blue | YN/B50 | varnish | YN/E50 | | | | |
| | STAN | DARD Colour R | ange (medium o | nacity) | | | | | |
| | | | 2 or YN/Z/ZM for so | • • • | 8 | | | | |
| | | | ndard shades upon re | | | | | | |
| citric yellow | YN 10/NT-NEU | carmine red | YN 22/NT-NEU | violet | YN 37/NT-NEU | | | | |
| medium yellow | YN 11/NT-NEU | pink | YN 25/NT-NEU | light green | YN 40/NT-NEU | | | | |
| dark yellow | YN 12/NT-NEU | light blue | YN 30/NT-NEU | fir green | YN 41/NT-NEU | | | | |
| orange | YN 15/NT-NEU | medium blue | YN 31/NT-NEU | brilliant green | YN 42/NT-NEU | | | | |
| ochre yellow | YN 17/NT-NEU | ultra marine | YN 32/NT-NEU | light brown | YN 50/NT-NEU | | | | |
| light red | YN 20/NT-NEU | dark blue | YN 33/NT-NEU | white | YN 60/NT-NEU | | | | |
| bright red | YN 21/NT-NEU | turquoise | YN 34/NT-NEU | black | YN 65/NT-NEU | | | | |
| | OT A N | DADD 0-1 D | | | | | | | |
| | | | ange HD (high o DARD HD for screen | | | | | | |
| | | | ard HD shades upon i | | | | | | |
| citric yellow, hig | | N 10/HD-NT-NEU | carmine red, hig | | YN 22/HD-NT-NEU | | | | |
| medium yellow, | • • • | N 11/HD-NT-NEU | light blue, highly opaque | | YN 30/HD-NT-NEU | | | | |
| dark yellow, hig | | N 12/HD-NT-NEU | light green, highly opaque | | YN 40/HD-NT-NEU | | | | |
| orange, highly o | | N 15/HD-NT-NEU | white, highly opaque | | YN 60/HD-NT-NEU | | | | |
| bright red, highly | | N 21/HD-NT-NEU | black, highly opaque | | YN 65/HD-NT-NEU | | | | |
| | | | | | | | | | |
| | SPECIAL PROD | | colour Shades, Vailability upon reques | | tes | | | | |
| white, matt | | N 60/MT-NT | bronze binder | | YN/B | | | | |
| transparent pas | te YI | N/TP | phosphorescent ink | | YN 96 | | | | |
| | _ | COLOUR PROC | EGO INIKO (OMV | IZ) | | | | | |
| | | | ESS INKS (CMY 2 or YN/YN/YNM for | • | ke | | | | |
| process yellow | | 'N 180/NT-NEU | process black | printing in | YN 65/NT-NEU | | | | |
| process yellow process magent | | 'N 181/NT-NEU | transparent paste | | YN/TP | | | | |
| process cyan | | 'N 182/NT-NEU | ' ' | | TIN/TF | | | | |
| process cyari | | TT TOZITT TILO | | | | | | | |
| | AB - BRO | | MG - METAL GI | LOSS INKS | | | | | |
| According to Bronze Colour Card | | | | | | | | | |
| AB Bronze Ink | S | | MG Metal Glo | ss Inks | | | | | |
| rich gold | | N 75/AB | rich gold | | YN 75/MG | | | | |
| rich pale gold | | 'N 76/AB | rich pale gold | | YN 76/MG | | | | |
| pale gold | | N 77/AB | pale gold | | YN 77/MG | | | | |
| copper | Y | N 78/AB | copper | | YN 78/MG | | | | |
| silver | Y | N 79/AB | silver | | YN 79/MG | | | | |

Matching of PMS, RAL, NCS colours and special shades upon request.

All above information refers to the colour shades listed in this product data sheet and other standard shades of this screen ink range. Information about availability of further standard shades upon request. In some individual cases the product characteristics of special colour shades and modifications of this ink type manufactured upon customer request may differ from the above properties.

Product data sheet screen ink YN

The statements in our product and safety data sheets are based on our present experiences, however they are no assurance of product properties and do not justify a contractual legal relationship. We provide these details to inform customers about our products and their possible applications. However, on account of various factors influencing processing of our products it is absolutely essential to carry out printing trials under local production conditions. Choice of individual ink types and their suitability for the intended application is the sole and entire responsibility of the user. We do not assume any liability for any problems of technical or process-related nature. Any liability shall be limited to the value of the goods delivered by us and processed by the user.

All former product data sheets are no longer valid.

January 2021 - Version B4

Coates Screen Inks GmbH
Wiederholdplatz 1 90451 Nürnberg
Tel.: 0911 6422 0 Fax: 0911 6422 200
http://www.coates.de